


B58_01_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B58_01_PRECRUSH\B58_01_PRECRUSH069.rdf
 Task file: C:\CamsizerXT\CAMSYS\B58_01_PRECRUSH.afg
 Time: 9/15/2015, 9:51, duration 12 min 59 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 15738921, CCD-Z = 277093
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.2	100.0	0.835	0.913	0.788	7
#20	#16	1.3	99.8	0.783	0.893	0.722	93
#30	#20	2.4	98.5	0.813	0.891	0.742	463
#40	#30	3.1	96.1	0.835	0.885	0.746	1701
#50	#40	4.7	93.0	0.868	0.887	0.756	8002
#60	#50	8.3	88.3	0.908	0.899	0.767	30167
#70	#60	13.5	80.0	0.915	0.904	0.751	74564
#140	#70	47.7	66.5	0.909	0.905	0.734	1008417
PAN	#140	18.8	18.8	0.894	0.921	0.726	31256414



Characteristics

Q3 [%]	x [μm]
10.0	87.2
50.0	174.4
90.0	326.1
SPAN3 = 1.370	
U3 = 2.260	
Mv3(x) = 208.7 μm	
Sigma3(x) = 162.2 μm	

Mean value SPHT3 = 0.893
 Mean value Symm3 = 0.905
 Mean value b/l3 = 0.724
 Mean value RDNS_C3 = 0.588
 Mean value SPHT_K3 = 0.646

User