


B58_2_5KCRUSH

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDAT\B58_2_5KCRUSH\B58_2_5KCRUSH054.rdf
Task file:	C:\CamsizerXT\CAMSYS\B58_2_5KCRUSH.afg
Time:	10/27/2015 , 15:06 , duration 29 min 55 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 60034286 , CCD-Z = 704276
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.395	0.699	0.689	1
#50	#40	0.1	100.0	0.753	0.802	0.735	455
#60	#50	1.5	99.9	0.866	0.866	0.768	10424
#70	#60	11.9	98.4	0.915	0.898	0.776	127179
#140	#70	73.9	86.5	0.910	0.904	0.736	2271935
PAN	#140	12.6	12.6	0.874	0.907	0.711	112515096



Mean value SPHT3 = 0.898
Mean value Symm3 = 0.902
Mean value b/l3 = 0.722
Mean value RDNS_C3 = 0.621
Mean value SPHT_K3 = 0.642

User