


B58\_2\_6KCRUSH

Company:  
 User:  
 Result file: C:\CamsizerXT\CAMDAT\B58\_2\_6KCRUSH\B58\_2\_6KCRUSH078.rdf  
 Task file: C:\CamsizerXT\CAMSYS\B58\_2\_6KCRUSH.afg  
 Time: 10/21/2015 , 13:07 , duration 28 min 2 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc\_min  
 No. of particles: CCD-B = 55144976 , CCD-Z = 636738  
 Velocity adaption: no  
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.676	0.771	0.792	3
#50	#40	0.1	100.0	0.734	0.783	0.730	453
#60	#50	1.9	99.9	0.873	0.869	0.770	12576
#70	#60	15.3	98.0	0.918	0.900	0.775	160548
#140	#70	72.0	82.7	0.911	0.905	0.734	1974713
PAN	#140	10.7	10.7	0.870	0.905	0.708	87247024



Mean value SPHT3 = 0.901  
 Mean value Symm3 = 0.902  
 Mean value b/l3 = 0.723  
 Mean value RDNS\_C3 = 0.618  
 Mean value SPHT\_K3 = 0.643

User