


**B59\_2\_PRECRUSH**

Company:  
 User:  
 Result file: C:\CamsizerXT\CAMDAT\B59\_2\_PRECRUSH\B59\_2\_PRECRUSH129.rdf  
 Task file: C:\CamsizerXT\CAMSYS\B59\_2\_PRECRUSH.afg  
 Time: 10/21/2015 , 13:55 , duration 14 min 3 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc\_min  
 No. of particles: CCD-B = 3157684 , CCD-Z = 37815  
 Velocity adaption: no  
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		1.5	100.0	0.746	0.888	0.742	27
#20	#16	3.2	98.5	0.780	0.891	0.715	152
#30	#20	4.9	95.3	0.805	0.889	0.732	637
#40	#30	4.9	90.4	0.825	0.886	0.738	1853
#50	#40	5.9	85.5	0.843	0.883	0.746	6567
#60	#50	3.8	79.6	0.858	0.879	0.749	8880
#70	#60	4.2	75.8	0.874	0.880	0.752	16962
#140	#70	49.2	71.6	0.893	0.902	0.747	1008216
PAN	#140	22.4	22.4	0.883	0.928	0.720	5886294



Mean value SPHT3 = 0.868  
 Mean value Symm3 = 0.902  
 Mean value b/l3 = 0.726  
 Mean value RDNS\_C3 = 0.560  
 Mean value SPHT\_K3 = 0.655

User