


B59_3_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B59_3_PRECRUSH\B59_3_PRECRUSH129.rdf
 Task file: C:\CamsizerXT\CAMSYS\B59_3_PRECRUSH.afg
 Time: 10/20/2015 , 13:01 , duration 17 min 5 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 3200027 , CCD-Z = 34970
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		3.4	100.0	0.800	0.910	0.786	87
#20	#16	3.9	96.6	0.814	0.902	0.773	264
#30	#20	4.0	92.7	0.817	0.898	0.767	721
#40	#30	3.8	88.7	0.821	0.888	0.767	2009
#50	#40	4.4	84.9	0.840	0.880	0.760	6677
#60	#50	3.5	80.5	0.861	0.878	0.757	11016
#70	#60	5.0	77.0	0.883	0.883	0.758	27142
#140	#70	54.1	72.0	0.893	0.901	0.742	1352495
PAN	#140	17.9	17.9	0.874	0.926	0.710	4854549



Characteristics

Q3 [%]	x [μm]
10.0	95.8
50.0	146.0
90.0	677.0
SPAN3 = 3.982	
U3 = 1.768	
Mv3(x) = 264.9 μm	
Sigma3(x) = 298.0 μm	

Mean value SPHT3 = 0.869
 Mean value Symm3 = 0.902
 Mean value b/l3 = 0.730
 Mean value RDNS_C3 = 0.547
 Mean value SPHT_K3 = 0.666

User