


B60_01_5KCRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B60_01_5KCRUSH\B60_01_5KCRUSH075.rdf
 Task file: C:\CamsizerXT\CAMSYS\B60_01_5KCRUSH.afg
 Time: 9/28/2015, 9:51, duration 26 min 36 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 44066387, CCD-Z = 662425
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.705	0.817	0.729	43
#50	#40	0.9	100.0	0.808	0.840	0.747	3283
#60	#50	8.2	99.1	0.903	0.893	0.771	57989
#70	#60	19.1	90.9	0.916	0.903	0.758	203160
#140	#70	63.0	71.8	0.911	0.906	0.736	2154733
PAN	#140	8.8	8.8	0.882	0.914	0.714	76702246



Characteristics

Q3 [%]	x [μm]
10.0	109.9
50.0	180.4
90.0	247.5
SPAN3 =	0.763
U3 =	1.771
Mv3(x) =	178.2 μm
Sigma3(x) =	56.0 μm

Mean value SPHT3 = 0.901
 Mean value Symm3 = 0.903
 Mean value b/l3 = 0.726
 Mean value RDNS_C3 = 0.632
 Mean value SPHT_K3 = 0.650

User