


B60_01_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B60_01_PRECRUSH\B60_01_PRECRUSH071.rdf
 Task file: C:\CamsizerXT\CAMSYS\B60_01_PRECRUSH.afg
 Time: 9/15/2015 , 10:19 , duration 11 min 44 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 15251814 , CCD-Z = 233611
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.1	100.0	0.909	0.924	0.864	1
#20	#16	0.1	99.9	0.799	0.890	0.748	6
#30	#20	0.8	99.8	0.812	0.885	0.741	102
#40	#30	2.6	99.0	0.836	0.886	0.747	938
#50	#40	9.3	96.4	0.891	0.896	0.766	9912
#60	#50	12.9	87.1	0.908	0.901	0.761	26805
#70	#60	16.4	74.2	0.913	0.903	0.750	55403
#140	#70	48.0	57.8	0.906	0.904	0.730	524458
PAN	#140	9.8	9.8	0.882	0.913	0.715	24530065



Characteristics

Q3 [%]	x [μm]
10.0	106.7
50.0	197.0
90.0	319.8
SPAN3 =	1.082
U3 =	2.029
Mv3(x) =	211.8 μm
Sigma3(x) =	113.7 μm

Mean value SPHT3 = 0.896
 Mean value Symm3 = 0.902
 Mean value b/l3 = 0.726
 Mean value RDNS_C3 = 0.585
 Mean value SPHT_K3 = 0.654

User