


B60_02_5KCRUSH

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDAT\B60_02_5KCRUSH\B60_02_5KCRUSH089.rdf
Task file:	C:\CamsizerXT\CAMSYS\B60_02_5KCRUSH.afg
Time:	10/5/2015 , 15:36 , duration 32 min 18 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 32614639 , CCD-Z = 478653
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.732	0.842	0.723	6
#50	#40	0.5	100.0	0.840	0.856	0.764	2236
#60	#50	7.4	99.5	0.913	0.899	0.778	54856
#70	#60	16.9	92.1	0.920	0.905	0.760	185885
#140	#70	64.3	75.2	0.912	0.907	0.742	2631803
PAN	#140	10.9	10.9	0.886	0.920	0.711	60718790



Mean value SPHT3 = 0.904
Mean value Symm3 = 0.906
Mean value b/l3 = 0.728
Mean value RDNS_C3 = 0.649
Mean value SPHT_K3 = 0.654

User