


**B60\_02\_6K CRUSH**

Company:  
 User:  
 Result file: C:\CamsizerXT\CAMDAT\B60\_02\_6K CRUSH\B60\_02\_6K CRUSH086.rdf  
 Task file: C:\CamsizerXT\CAMSYS\B60\_02\_6K CRUSH.afg  
 Time: 9/30/2015, 15:07, duration 35 min 46 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc\_min  
 No. of particles: CCD-B = 41179555, CCD-Z = 603675  
 Velocity adaption: no  
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.0	100.0	0.729	0.792	0.725	191
#60	#50	1.0	100.0	0.882	0.876	0.775	8063
#70	#60	8.7	99.0	0.919	0.902	0.774	108216
#140	#70	76.2	90.3	0.913	0.907	0.746	3623030
PAN	#140	14.1	14.1	0.892	0.922	0.711	76075652



Mean value SPHT3 = 0.904  
 Mean value Symm3 = 0.907  
 Mean value b/l3 = 0.728  
 Mean value RDNS\_C3 = 0.661  
 Mean value SPHT\_K3 = 0.652

User