


B60\_02\_PRECRUSH

Company:  
 User:  
 Result file: C:\CamsizerXT\CAMDAT\B60\_02\_PRECRUSH\B60\_02\_PRECRUSH081.rdf  
 Task file: C:\CamsizerXT\CAMSYS\B60\_02\_PRECRUSH.afg  
 Time: 9/18/2015 , 11:59 , duration 9 min 51 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc\_min  
 No. of particles: CCD-B = 3810699 , CCD-Z = 68721  
 Velocity adaption: no  
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.5	100.0	0.821	0.899	0.739	16
#20	#16	1.3	99.5	0.796	0.895	0.698	100
#30	#20	2.1	98.2	0.811	0.887	0.716	464
#40	#30	2.8	96.1	0.838	0.888	0.726	1781
#50	#40	7.5	93.3	0.888	0.896	0.760	14577
#60	#50	9.7	85.8	0.909	0.901	0.761	38852
#70	#60	12.7	76.1	0.916	0.904	0.752	80336
#140	#70	51.9	63.4	0.905	0.906	0.740	1336751
PAN	#140	11.5	11.5	0.882	0.927	0.709	10095637



Mean value SPHT3 = 0.892  
 Mean value Symm3 = 0.904  
 Mean value b/l3 = 0.725  
 Mean value RDNS\_C3 = 0.598  
 Mean value SPHT\_K3 = 0.647

User