


B61_2_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B61_2_PRECRUSH\B61_2_PRECRUSH075.rdf
 Task file: C:\CamsizerXT\CAMSYS\B61_2_PRECRUSH.afg
 Time: 9/17/2015, 8:07, duration 12 min 55 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 18032510, CCD-Z = 180001
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0	0.794	0.852	0.794	12
#30	#20	1.1	100.0	0.819	0.864	0.751	669
#40	#30	14.7	98.9	0.882	0.892	0.763	24736
#50	#40	49.2	84.2	0.906	0.907	0.747	188459
#60	#50	13.5	35.0	0.900	0.906	0.717	103684
#70	#60	7.4	21.5	0.908	0.904	0.734	100475
#140	#70	12.1	14.1	0.905	0.906	0.721	429548
PAN	#140	2.0	2.0	0.863	0.913	0.720	44877962



Characteristics

Q3 [%]	x [μm]
10.0	191.2
50.0	335.8
90.0	453.9
SPAN3 =	0.782
U3 =	1.870
Mv3(x) =	330.7 μm
Sigma3(x) =	106.6 μm

Mean value SPHT3 = 0.894
 Mean value Symm3 = 0.903
 Mean value b/l3 = 0.726
 Mean value RDNS_C3 = 0.577
 Mean value SPHT_K3 = 0.656

User