


B62_02_5KCRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B62_02_5KCRUSH\B62_02_5KCRUSH155.rdf
 Task file: C:\CamsizerXT\CAMSYS\B62_02_5KCRUSH.afg
 Time: 12/21/2015 , 14:42 , duration 19 min 13 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 61196531 , CCD-Z = 721569
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.664	0.770	0.785	5
#40	#30	1.8	100.0	0.908	0.899	0.797	7276
#50	#40	28.6	98.2	0.919	0.907	0.771	269563
#60	#50	32.1	69.6	0.920	0.909	0.754	573765
#70	#60	21.6	37.5	0.916	0.909	0.730	582348
#140	#70	13.1	15.9	0.892	0.902	0.688	884637
PAN	#140	2.8	2.8	0.851	0.903	0.681	114172544



Characteristics

Q3 [%]	x [μm]
10.0	190.6
50.0	267.6
90.0	358.2
SPAN3 =	0.626
U3 =	1.484
Mv3(x) =	269.1 μm
Sigma3(x) =	72.3 μm

Mean value SPHT3 = 0.907
 Mean value Symm3 = 0.906
 Mean value b/l3 = 0.729
 Mean value RDNS_C3 = 0.685
 Mean value SPHT_K3 = 0.657

User