


B62_02_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B62_02_PRECRUSH\B62_02_PRECRUSH138.rdf
 Task file: C:\CamsizerXT\CAMSYS\B62_02_PRECRUSH.afg
 Time: 12/17/2015 , 14:02 , duration 8 min 10 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 2907100 , CCD-Z = 64219
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		1.6	100.0	0.724	0.880	0.702	98
#20	#16	1.7	98.4	0.749	0.879	0.728	267
#30	#20	2.1	96.7	0.794	0.874	0.731	1004
#40	#30	5.3	94.6	0.862	0.884	0.758	7552
#50	#40	23.4	89.3	0.905	0.900	0.759	93669
#60	#50	22.0	65.9	0.913	0.905	0.744	169748
#70	#60	18.6	43.9	0.916	0.907	0.735	231828
#140	#70	25.1	25.3	0.909	0.908	0.717	741575
PAN	#140	0.2	0.2	0.853	0.917	0.654	7447609



Characteristics

Q3 [%]	x [μm]
10.0	174.7
50.0	262.8
90.0	435.7
SPAN3 = 0.993	
U3 = 1.631	
Mv3(x) = 309.1 μm	
Sigma3(x) = 197.6 μm	

Mean value SPHT3 = 0.894
 Mean value Symm3 = 0.901
 Mean value b/l3 = 0.724
 Mean value RDNS_C3 = 0.602
 Mean value SPHT_K3 = 0.647

User