


B62_03_5KCRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B62_03_5KCRUSH\B62_03_5KCRUSH151.rdf
 Task file: C:\CamsizerXT\CAMSYS\B62_03_5KCRUSH.afg
 Time: 12/21/2015 , 13:11 , duration 24 min 11 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 47475158 , CCD-Z = 845728
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.539	0.652	0.778	2
#50	#40	0.1	100.0	0.711	0.756	0.724	476
#60	#50	1.8	99.9	0.888	0.878	0.774	22265
#70	#60	17.8	98.1	0.923	0.905	0.772	326014
#140	#70	74.7	80.3	0.916	0.909	0.736	3553635
PAN	#140	5.6	5.6	0.874	0.913	0.701	92529980



Characteristics

Q3 [%]	x [μm]
10.0	122.4
50.0	181.0
90.0	225.5
SPAN3 = 0.570	
U3 = 1.560	
Mv3(x) = 176.1 μm	
Sigma3(x) = 42.9 μm	

Mean value SPHT3 = 0.908
 Mean value Symm3 = 0.906
 Mean value b/l3 = 0.726
 Mean value RDNS_C3 = 0.639
 Mean value SPHT_K3 = 0.647

User