


CHOT\_01\_SV\_14\_SHERE\_AND\_ROUND

Company:  
 User:  
 Result file: C:\...DAT\CHOT\_01\_SV\_14\_SHERE\_AND\_ROUND\CHOT\_01\_SV\_14\_SHERE\_AND\_ROUND171.rdf  
 Task file: C:\CamsizerXT\CAMSYS\CHOT\_01\_SV\_14\_SHERE\_AND\_ROUND.afg  
 Time: 6/16/2015, 14:38, duration 3 min 4 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc\_min  
 No. of particles: CCD-B = 824714, CCD-Z = 16163  
 Velocity adaption: no  
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.561	0.699	0.712	21
#50	#40	3.6	100.0	0.850	0.859	0.755	6070
#60	#50	39.9	96.4	0.902	0.897	0.759	114243
#70	#60	43.3	56.5	0.905	0.903	0.722	171154
#140	#70	13.2	13.2	0.868	0.898	0.626	74727
PAN	#140	0.0	0.0	0.829	0.899	0.707	2226246



Mean value SPHT3 = 0.890  
 Mean value Symm3 = 0.896  
 Mean value b/l3 = 0.711  
 Mean value RDNS\_C3 = 0.540  
 Mean value SPHT\_K3 = 0.619

User