


B63_04_CRUSH5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B63_04_CRUSH5K\B63_04_CRUSH5K114.rdf
 Task file: C:\CamsizerXT\CAMSYS\B63_04_CRUSH5K.afg
 Time: 6/11/2015, 14:18, duration 12 min 37 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 10978339, CCD-Z = 116111
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0	0.674	0.838	0.728	2
#30	#20	0.1	100.0	0.641	0.737	0.735	49
#40	#30	19.1	99.9	0.900	0.901	0.777	55618
#50	#40	71.4	80.8	0.909	0.912	0.741	367379
#60	#50	5.3	9.4	0.887	0.906	0.679	53574
#70	#60	1.3	4.1	0.879	0.894	0.685	23537
#140	#70	1.9	2.8	0.848	0.885	0.651	115631
PAN	#140	0.9	0.9	0.789	0.887	0.612	33685254



Mean value SPHT3 = 0.898
 Mean value Symm3 = 0.907
 Mean value b/l3 = 0.728
 Mean value RDNS_C3 = 0.577
 Mean value SPHT_K3 = 0.660

User