


B63_04_SV_14_CRUSH_6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B63_04_SV_14_CRUSH_6K\B63_04_SV_14_CRUSH_6K108.rdf
 Task file: C:\CamsizerXT\CAMSYS\B63_04_SV_14_CRUSH_6K.afg
 Time: 6/11/2015, 12:17, duration 12 min 47 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 27037729, CCD-Z = 247082
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0	0.648	0.694	0.764	3
#30	#20	4.1	100.0	0.883	0.895	0.789	5325
#40	#30	46.0	95.9	0.901	0.908	0.761	124881
#50	#40	38.6	49.9	0.904	0.910	0.737	241722
#60	#50	4.3	11.3	0.884	0.899	0.697	59664
#70	#60	1.8	7.0	0.873	0.889	0.687	42017
#140	#70	3.2	5.2	0.842	0.883	0.647	244666
PAN	#140	2.0	2.0	0.797	0.891	0.632	63469143



Characteristics

Q3 [%]	x [μm]
10.0	289.1
50.0	425.2
90.0	559.6
SPAN3 = 0.636	
U3 = 1.564	
Mv3(x) = 420.3 μm	
Sigma3(x) = 114.8 μm	

Mean value SPHT3 = 0.891
 Mean value Symm3 = 0.905
 Mean value b/l3 = 0.730
 Mean value RDNS_C3 = 0.550
 Mean value SPHT_K3 = 0.667

User