


B63_2_SV_14_CRUSH5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B63_2_SV_14_CRUSH5K\B63_2_SV_14_CRUSH5K111.rdf
 Task file: C:\CamsizerXT\CAMSYS\B63_2_SV_14_CRUSH5K.afg
 Time: 6/10/2015, 11:51, duration 18 min 10 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 51010276, CCD-Z = 90769
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0	0.353	0.717	0.595	2
#20	#16	0.0	100.0	0.522	0.828	0.574	1
#30	#20	0.1	100.0	0.608	0.765	0.719	12
#40	#30	5.4	99.9	0.901	0.897	0.791	17250
#50	#40	51.3	94.5	0.912	0.907	0.761	342742
#60	#50	22.4	43.2	0.910	0.909	0.733	282379
#70	#60	7.9	20.8	0.901	0.904	0.710	159250
#140	#70	9.1	12.9	0.880	0.894	0.700	604108
PAN	#140	3.8	3.8	0.780	0.870	0.618	66382663



Mean value SPHT3 = 0.897
 Mean value Symm3 = 0.903
 Mean value b/l3 = 0.728
 Mean value RDNS_C3 = 0.626
 Mean value SPHT_K3 = 0.659

User