


B63_2_SV_14_CRUSH6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B63_2_SV_14_CRUSH6K\B63_2_SV_14_CRUSH6K108.rdf
 Task file: C:\CamsizerXT\CAMSYS\B63_2_SV_14_CRUSH6K.afg
 Time: 6/9/2015 , 14:13 , duration 18 min 30 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 46636884 , CCD-Z = 580279
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.640	0.634	0.764	4
#40	#30	5.5	100.0	0.904	0.899	0.793	12473
#50	#40	50.8	94.5	0.912	0.908	0.761	237633
#60	#50	21.3	43.7	0.909	0.908	0.733	191287
#70	#60	7.9	22.4	0.901	0.903	0.713	113430
#140	#70	10.2	14.5	0.885	0.895	0.701	484143
PAN	#140	4.3	4.3	0.838	0.897	0.665	70363361



Characteristics

Q3 [%]	x [μm]
10.0	176.7
50.0	311.8
90.0	404.6
SPAN3 =	0.731
U3 =	1.871
Mv3(x) =	301.1 μm
Sigma3(x) =	90.2 μm

Mean value SPHT3 = 0.899
 Mean value Symm3 = 0.905
 Mean value b/l3 = 0.729
 Mean value RDNS_C3 = 0.640
 Mean value SPHT_K3 = 0.662

User