


B63_2_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B63_2_SV_14_PRECRUSH\B63_2_SV_14_PRECRUSH100.rdf
 Task file: C:\CamsizerXT\CAMSYS\B63_2_SV_14_PRECRUSH.afg
 Time: 6/8/2015 , 13:05 , duration 8 min 41 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 1905564 , CCD-Z = 28613
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		2.4	100.0	0.739	0.878	0.742	210
#20	#16	3.7	97.6	0.767	0.871	0.739	832
#30	#20	7.4	93.9	0.824	0.876	0.752	4804
#40	#30	18.3	86.5	0.868	0.885	0.751	33185
#50	#40	33.9	68.2	0.899	0.900	0.744	160115
#60	#50	14.7	34.3	0.909	0.906	0.731	143419
#70	#60	9.1	19.6	0.914	0.909	0.728	147393
#140	#70	10.4	10.5	0.907	0.909	0.712	400077
PAN	#140	0.1	0.1	0.835	0.905	0.654	6204221



Characteristics

Q3 [%]	x [μm]
10.0	209.7
50.0	350.3
90.0	683.4
SPAN3 = 1.352	
U3 = 1.845	
Mv3(x) = 413.3 μm	
Sigma3(x) = 238.2 μm	

Mean value SPHT3 = 0.878
 Mean value Symm3 = 0.895
 Mean value b/l3 = 0.725
 Mean value RDNS_C3 = 0.562
 Mean value SPHT_K3 = 0.661

User