


B63_3_CRUSH5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B63_3_CRUSH5K\B63_3_CRUSH5K110.rdf
 Task file: C:\CamsizerXT\CAMSYS\B63_3_CRUSH5K.afg
 Time: 6/10/2015, 16:03, duration 17 min 39 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 48725598, CCD-Z = 368442
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0	0.421	0.754	0.427	1
#30	#20	3.3	100.0	0.880	0.893	0.791	2904
#40	#30	36.9	96.7	0.895	0.903	0.765	69364
#50	#40	39.0	59.8	0.897	0.903	0.741	174180
#60	#50	7.0	20.8	0.884	0.896	0.707	67325
#70	#60	3.2	13.8	0.879	0.891	0.699	53024
#140	#70	6.1	10.6	0.854	0.883	0.668	332916
PAN	#140	4.5	4.5	0.802	0.879	0.623	101963994



Characteristics

Q3 [%]	x [μm]
10.0	204.0
50.0	396.4
90.0	544.5
SPAN3 = 0.859	
U3 = 2.086	
Mv3(x) = 385.8 μm	
Sigma3(x) = 132.1 μm	

Mean value SPHT3 = 0.883
 Mean value Symm3 = 0.899
 Mean value b/l3 = 0.725
 Mean value RDNS_C3 = 0.523
 Mean value SPHT_K3 = 0.660

User