


B63\_3\_CRUSH6K

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDAT\B63_3_CRUSH6K\B63_3_CRUSH6K109.rdf
Task file:	C:\CamsizerXT\CAMSYS\B63_3_CRUSH6K.afg
Time:	6/10/2015 , 10:39 , duration 25 min 16 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 66101279 , CCD-Z = 514813
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	3.1	100.0	0.882	0.896	0.791	2698
#40	#30	35.8	96.9	0.896	0.904	0.766	64891
#50	#40	36.8	61.1	0.897	0.903	0.743	159929
#60	#50	7.2	24.3	0.885	0.896	0.713	69055
#70	#60	3.8	17.1	0.880	0.890	0.703	59133
#140	#70	7.6	13.3	0.854	0.882	0.669	411578
PAN	#140	5.7	5.7	0.809	0.881	0.631	126636712



Mean value SPHT3 = 0.882
Mean value Symm3 = 0.899
Mean value b/l3 = 0.724
Mean value RDNS_C3 = 0.522
Mean value SPHT_K3 = 0.658

User