


B64_02_CRUSH6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B64_02_CRUSH6K\B64_02_CRUSH6K052.rdf
 Task file: C:\CamsizerXT\CAMSYS\B64_02_CRUSH6K.afg
 Time: 6/22/2015 , 14:48 , duration 30 min 4 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 140063448 , CCD-Z = 1271406
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0	0.477	0.798	0.602	4
#20	#16	0.1	100.0	0.599	0.832	0.653	24
#30	#20	0.5	99.9	0.670	0.832	0.703	340
#40	#30	1.4	99.4	0.727	0.838	0.709	3126
#50	#40	3.6	98.0	0.770	0.834	0.710	21617
#60	#50	3.1	94.4	0.813	0.842	0.708	36618
#70	#60	7.8	91.3	0.886	0.882	0.753	167644
#140	#70	74.0	83.5	0.914	0.907	0.747	4635381
PAN	#140	9.5	9.5	0.873	0.906	0.722	209283452



Characteristics

Q3 [%]	x [μm]
10.0	108.5
50.0	168.6
90.0	238.4
SPAN3 = 0.770	
U3 = 1.645	
Mv3(x) = 177.6 μm	
Sigma3(x) = 87.3 μm	

Mean value SPHT3 = 0.889
 Mean value Symm3 = 0.897
 Mean value b/l3 = 0.726
 Mean value RDNS_C3 = 0.554
 Mean value SPHT_K3 = 0.658

User