


B64_02_CRUSH7K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B64_02_CRUSH7K\B64_02_CRUSH7K053.rdf
 Task file: C:\CamsizerXT\CAMSYS\B64_02_CRUSH7K.afg
 Time: 6/22/2015 , 15:31 , duration 39 min 39 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 182257370 , CCD-Z = 1505092
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0	0.642	0.847	0.698	10
#30	#20	0.3	100.0	0.726	0.856	0.723	201
#40	#30	1.0	99.7	0.757	0.848	0.717	2081
#50	#40	2.6	98.7	0.792	0.844	0.718	14904
#60	#50	2.5	96.1	0.829	0.853	0.718	28456
#70	#60	7.1	93.6	0.894	0.887	0.762	143678
#140	#70	73.8	86.5	0.916	0.908	0.750	4445681
PAN	#140	12.7	12.7	0.869	0.902	0.719	248085253



Characteristics

Q3 [%]	x [μm]
10.0	87.4
50.0	164.8
90.0	223.9
SPAN3 =	0.828
U3 =	1.993
Mv3(x) =	167.0 μm
Sigma3(x) =	74.1 μm

Mean value SPHT3 = 0.895
 Mean value Symm3 = 0.900
 Mean value b/l3 = 0.730
 Mean value RDNS_C3 = 0.566
 Mean value SPHT_K3 = 0.666

User