


B65_02_CRUSH5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B65_02_CRUSH5K\B65_02_CRUSH5K060.rdf
 Task file: C:\CamsizerXT\CAMSYS\B65_02_CRUSH5K.afg
 Time: 6/23/2015, 14:21, duration 25 min 27 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 64374699, CCD-Z = 777837
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0	0.359	0.755	0.792	1
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.612	0.860	0.518	1
#40	#30	0.1	100.0	0.709	0.826	0.731	68
#50	#40	0.4	99.9	0.748	0.815	0.720	1968
#60	#50	1.4	99.5	0.838	0.852	0.745	11590
#70	#60	8.3	98.1	0.913	0.896	0.773	113151
#140	#70	78.6	89.8	0.919	0.909	0.753	3769839
PAN	#140	11.2	11.2	0.893	0.917	0.732	108596332



Characteristics

Q3 [%]	x [μm]
10.0	102.7
50.0	154.3
90.0	212.4
SPAN3 =	0.711
U3 =	1.624
Mv3(x) =	155.6 μm
Sigma3(x) =	49.2 μm

Mean value SPHT3 = 0.907
 Mean value Symm3 = 0.906
 Mean value b/l3 = 0.737
 Mean value RDNS_C3 = 0.672
 Mean value SPHT_K3 = 0.675

User