


B65_02_CRUSH6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B65_02_CRUSH6K\B65_02_CRUSH6K055.rdf
 Task file: C:\CamsizerXT\CAMSYS\B65_02_CRUSH6K.afg
 Time: 6/23/2015, 12:10, duration 25 min 15 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 70659607, CCD-Z = 5508728
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.738	0.835	0.718	32
#50	#40	0.3	100.0	0.771	0.829	0.726	965
#60	#50	1.0	99.7	0.853	0.860	0.759	8248
#70	#60	7.5	98.7	0.917	0.899	0.777	95358
#140	#70	76.7	91.2	0.924	0.910	0.754	3489600
PAN	#140	14.5	14.5	0.913	0.923	0.746	733504609



Characteristics

Q3 [%]	x [μm]
10.0	94.0
50.0	150.1
90.0	209.2
SPAN3 = 0.768	
U3 = 1.739	
Mv3(x) = 150.5 μm	
Sigma3(x) = 47.8 μm	

Mean value SPHT3 = 0.915
 Mean value Symm3 = 0.909
 Mean value b/l3 = 0.740
 Mean value RDNS_C3 = 0.705
 Mean value SPHT_K3 = 0.679

User