


B66_01_CRUSH5K

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDAT\B66_01_CRUSH5K\B66_01_CRUSH5K050.rdf
Task file:	C:\CamsizerXT\CAMSYS\B66_01_CRUSH5K.afg
Time:	6/22/2015 , 13:48 , duration 17 min 32 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 48588050 , CCD-Z = 413754
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.679	0.775	0.750	28
#40	#30	2.4	100.0	0.854	0.864	0.771	11163
#50	#40	41.2	97.6	0.907	0.901	0.762	454752
#60	#50	33.3	56.4	0.912	0.908	0.735	660633
#70	#60	13.8	23.1	0.904	0.908	0.703	408654
#140	#70	7.1	9.3	0.880	0.897	0.679	613106
PAN	#140	2.2	2.2	0.825	0.897	0.666	103866324



Mean value SPHT3 = 0.897
Mean value Symm3 = 0.902
Mean value b/l3 = 0.722
Mean value RDNS_C3 = 0.642
Mean value SPHT_K3 = 0.643

User