


B66_01_CRUSH6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B66_01_CRUSH6K\B66_01_CRUSH6K049.rdf
 Task file: C:\CamsizerXT\CAMSYS\B66_01_CRUSH6K.afg
 Time: 6/22/2015, 13:18, duration 18 min 17 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 49641943, CCD-Z = 434151
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.661	0.780	0.744	19
#40	#30	2.2	100.0	0.857	0.867	0.774	10449
#50	#40	40.7	97.8	0.908	0.901	0.763	446740
#60	#50	33.1	57.1	0.912	0.908	0.735	653518
#70	#60	14.0	24.0	0.904	0.907	0.704	413696
#140	#70	7.8	10.0	0.879	0.897	0.680	659631
PAN	#140	2.2	2.2	0.828	0.897	0.666	95108024



Mean value SPHT3 = 0.897
 Mean value Symm3 = 0.902
 Mean value b/l3 = 0.722
 Mean value RDNS_C3 = 0.642
 Mean value SPHT_K3 = 0.643

User