


B66_01_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B66_01_PRECRUSH\B66_01_PRECRUSH049.rdf
 Task file: C:\CamsizerXT\CAMSYS\B66_01_PRECRUSH.afg
 Time: 6/19/2015 , 13:30 , duration 7 min 46 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 10463997 , CCD-Z = 131316
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		3.7	100.0	0.717	0.870	0.728	367
#20	#16	5.4	96.3	0.737	0.862	0.719	1286
#30	#20	6.9	90.9	0.764	0.853	0.718	4759
#40	#30	10.7	84.0	0.816	0.855	0.728	21307
#50	#40	34.9	73.3	0.895	0.894	0.746	201179
#60	#50	22.4	38.4	0.908	0.906	0.725	239120
#70	#60	10.0	16.0	0.904	0.908	0.701	170639
#140	#70	5.7	6.0	0.896	0.905	0.689	219079
PAN	#140	0.3	0.3	0.860	0.908	0.718	19160229



Characteristics

Q3 [%]	x [μm]
10.0	230.8
50.0	326.2
90.0	808.1
SPAN3 =	1.770
U3 =	1.539
Mv3(x) =	424.1 μm
Sigma3(x) =	270.1 μm

Mean value SPHT3 = 0.860
 Mean value Symm3 = 0.888
 Mean value b/l3 = 0.713
 Mean value RDNS_C3 = 0.512
 Mean value SPHT_K3 = 0.635

User