


B65_02_CRUSH5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B65_02_CRUSH5K\B65_02_CRUSH5K040.rdf
 Task file: C:\CamsizerXT\CAMSYS\B65_02_CRUSH5K.afg
 Time: 6/17/2015 , 10:18 , duration 20 min 8 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 68571967 , CCD-Z = 617277
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.591	0.670	0.726	40
#50	#40	1.9	100.0	0.869	0.865	0.772	22283
#60	#50	30.0	98.1	0.925	0.908	0.780	635800
#70	#60	41.0	68.1	0.925	0.912	0.747	1192292
#140	#70	23.1	27.1	0.897	0.904	0.691	1542787
PAN	#140	4.0	4.0	0.840	0.900	0.673	139043029



Characteristics

Q3 [%]	x [μm]
10.0	168.1
50.0	235.1
90.0	274.4
SPAN3 =	0.452
U3 =	1.447
Mv3(x) =	226.0 μm
Sigma3(x) =	49.7 μm

Mean value SPHT3 = 0.909
 Mean value Symm3 = 0.906
 Mean value b/l3 = 0.728
 Mean value RDNS_C3 = 0.586
 Mean value SPHT_K3 = 0.654

User