


B66_02_CRUSH6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B66_02_CRUSH6K\B66_02_CRUSH6K038.rdf
 Task file: C:\CamsizerXT\CAMSYS\B66_02_CRUSH6K.afg
 Time: 6/17/2015, 9:39, duration 21 min 55 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 103366353, CCD-Z = 879655
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0	0.883	0.938	0.760	2
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.677	0.766	0.734	59
#50	#40	1.5	100.0	0.867	0.866	0.773	17445
#60	#50	26.8	98.5	0.925	0.908	0.782	556800
#70	#60	39.5	71.7	0.925	0.912	0.751	1141184
#140	#70	26.1	32.2	0.899	0.904	0.699	1828755
PAN	#140	6.1	6.1	0.849	0.902	0.680	183799014



Characteristics

Q3 [%]	x [μm]
10.0	142.5
50.0	230.8
90.0	271.4
SPAN3 =	0.558
U3 =	1.681
Mv3(x) =	218.5 μm
Sigma3(x) =	56.1 μm

Mean value SPHT3 = 0.907
 Mean value Symm3 = 0.906
 Mean value b/l3 = 0.729
 Mean value RDNS_C3 = 0.580
 Mean value SPHT_K3 = 0.656

User