


B66_03_CRUSH5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B66_03_CRUSH5K\B66_03_CRUSH5K045.rdf
 Task file: C:\CamsizerXT\CAMSYS\B66_03_CRUSH5K.afg
 Time: 6/19/2015 , 11:37 , duration 24 min 18 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 72374679 , CCD-Z = 812214
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.798	0.862	0.741	1
#50	#40	0.1	100.0	0.733	0.798	0.741	462
#60	#50	0.6	99.9	0.860	0.861	0.772	10215
#70	#60	6.6	99.3	0.912	0.895	0.777	156500
#140	#70	84.6	92.7	0.913	0.908	0.742	6459174
PAN	#140	8.1	8.1	0.863	0.909	0.688	156261189



Characteristics

Q3 [%]	x [μm]
10.0	111.3
50.0	156.8
90.0	205.6
SPAN3 =	0.601
U3 =	1.499
Mv3(x) =	156.2 μm
Sigma3(x) =	40.3 μm

Mean value SPHT3 = 0.902
 Mean value Symm3 = 0.905
 Mean value b/l3 = 0.725
 Mean value RDNS_C3 = 0.613
 Mean value SPHT_K3 = 0.647

User