


B66_03_PRECRUSH

| | |
|--------------------|---|
| Company: | |
| User: | |
| Result file: | C:\CamsizerXT\CAMDAT\B66_03_PRECRUSH\B66_03_PRECRUSH041.rdf |
| Task file: | C:\CamsizerXT\CAMSYS\B66_03_PRECRUSH.afg |
| Time: | 6/17/2015 , 10:49 , duration 9 min 54 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm |
| Particle model: | xc_min |
| No. of particles: | CCD-B = 7409159 , CCD-Z = 165044 |
| Velocity adaption: | no |
| Fitting: | no |
| Material: | |

| ASTM(+) | No(-) | retained [%] | passing [%] | SPHT3 | Symm3 | b/l3 | PDN |
|---------|-------|--------------|-------------|-------|-------|-------|----------|
| > #16 | | 3.6 | 100.0 | 0.738 | 0.884 | 0.748 | 317 |
| #20 | #16 | 5.3 | 96.4 | 0.754 | 0.880 | 0.734 | 1115 |
| #30 | #20 | 6.7 | 91.1 | 0.773 | 0.874 | 0.735 | 3968 |
| #40 | #30 | 8.2 | 84.4 | 0.795 | 0.868 | 0.734 | 13792 |
| #50 | #40 | 10.7 | 76.2 | 0.825 | 0.864 | 0.732 | 51270 |
| #60 | #50 | 8.0 | 65.5 | 0.857 | 0.870 | 0.733 | 81781 |
| #70 | #60 | 10.4 | 57.5 | 0.890 | 0.885 | 0.739 | 174937 |
| #140 | #70 | 45.6 | 47.1 | 0.905 | 0.907 | 0.729 | 2383610 |
| PAN | #140 | 1.5 | 1.5 | 0.878 | 0.930 | 0.678 | 31868214 |



| |
|----------------------------|
| Mean value SPHT3 = 0.854 |
| Mean value Symm3 = 0.888 |
| Mean value b/l3 = 0.718 |
| Mean value RDNS_C3 = 0.394 |
| Mean value SPHT_K3 = 0.648 |

User