


B67_01_CRUSH6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B67_01_CRUSH6K\B67_01_CRUSH6K044.rdf
 Task file: C:\CamsizerXT\CAMSYS\B67_01_CRUSH6K.afg
 Time: 6/19/2015 , 11:10 , duration 24 min 35 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 71826738 , CCD-Z = 605885
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.882	0.928	0.712	1
#40	#30	0.0	100.0	0.829	0.888	0.729	3
#50	#40	0.1	100.0	0.684	0.737	0.725	703
#60	#50	1.8	99.9	0.885	0.876	0.776	35431
#70	#60	19.4	98.1	0.927	0.907	0.780	571316
#140	#70	73.9	78.7	0.920	0.910	0.737	4711754
PAN	#140	4.8	4.8	0.845	0.901	0.676	131016810



Characteristics

Q3 [%]	x [μm]
10.0	135.6
50.0	187.8
90.0	226.2
SPAN3 =	0.482
U3 =	1.443
Mv3(x) =	182.9 μm
Sigma3(x) =	40.3 μm

Mean value SPHT3 = 0.911
 Mean value Symm3 = 0.907
 Mean value b/l3 = 0.729
 Mean value RDNS_C3 = 0.584
 Mean value SPHT_K3 = 0.656

User