


B67_01_CRUSH8K_3

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B67_01_CRUSH8K_3\B67_01_CRUSH8K_3077.rdf
 Task file: C:\CamsizerXT\CAMSYS\B67_01_CRUSH8K_3.afg
 Time: 7/2/2015, 14:58, duration 24 min 16 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 128884387, CCD-Z = 1067001
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.782	0.844	0.711	6
#50	#40	0.1	100.0	0.672	0.732	0.717	691
#60	#50	1.8	99.9	0.879	0.873	0.774	32416
#70	#60	18.3	98.1	0.924	0.905	0.780	511534
#140	#70	71.3	79.8	0.919	0.909	0.740	4511363
PAN	#140	8.5	8.5	0.863	0.904	0.698	205160064



Characteristics

Q3 [%]	x [μm]
10.0	115.9
50.0	184.9
90.0	225.4
SPAN3 = 0.592	
U3 = 1.670	
Mv3(x) = 176.6 μm	
Sigma3(x) = 47.1 μm	

Mean value SPHT3 = 0.909
 Mean value Symm3 = 0.906
 Mean value b/l3 = 0.730
 Mean value RDNS_C3 = 0.622
 Mean value SPHT_K3 = 0.659

User