


B67_01_CRUSH9K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B67_01_CRUSH9K\B67_01_CRUSH9K059.rdf
 Task file: C:\CamsizerXT\CAMSYS\B67_01_CRUSH9K.afg
 Time: 6/23/2015, 13:48, duration 26 min 39 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 81410923, CCD-Z = 918631
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.702	0.793	0.748	2
#50	#40	0.1	100.0	0.727	0.771	0.727	359
#60	#50	1.5	99.9	0.881	0.875	0.775	12247
#70	#60	17.5	98.4	0.926	0.907	0.782	216121
#140	#70	70.8	80.9	0.920	0.910	0.742	1989541
PAN	#140	10.1	10.1	0.859	0.901	0.692	107820598



Characteristics

Q3 [%]	x [μm]
10.0	104.9
50.0	183.8
90.0	224.0
SPAN3 =	0.648
U3 =	1.835
Mv3(x) =	173.9 μm
Sigma3(x) =	49.1 μm

Mean value SPHT3 = 0.909
 Mean value Symm3 = 0.906
 Mean value b/l3 = 0.730
 Mean value RDNS_C3 = 0.598
 Mean value SPHT_K3 = 0.661

User