


B67_01_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B67_01_PRECRUSH\B67_01_PRECRUSH047.rdf
 Task file: C:\CamsizerXT\CAMSYS\B67_01_PRECRUSH.afg
 Time: 6/17/2015 , 14:38 , duration 11 min 9 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 4293630 , CCD-Z = 93101
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.9	100.0	0.769	0.896	0.783	67
#20	#16	1.2	99.1	0.758	0.878	0.743	243
#30	#20	1.3	97.9	0.776	0.871	0.740	726
#40	#30	2.2	96.6	0.790	0.855	0.739	3689
#50	#40	7.2	94.4	0.837	0.856	0.739	34240
#60	#50	12.8	87.2	0.894	0.887	0.750	124077
#70	#60	25.1	74.4	0.920	0.906	0.755	390394
#140	#70	49.0	49.3	0.917	0.911	0.724	1575023
PAN	#140	0.3	0.3	0.866	0.921	0.685	15171041



Characteristics

Q3 [%]	x [μm]
10.0	164.2
50.0	212.8
90.0	327.4
SPAN3 =	0.767
U3 =	1.372
Mv3(x) =	250.9 μm
Sigma3(x) =	163.7 μm

Mean value SPHT3 = 0.894
 Mean value Symm3 = 0.899
 Mean value b/l3 = 0.722
 Mean value RDNS_C3 = 0.477
 Mean value SPHT_K3 = 0.644

User