


B67_02_CRUSH6k

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B67_02_CRUSH6k\B67_02_CRUSH6k106.rdf
 Task file: C:\CamsizerXT\CAMSYS\B67_02_CRUSH6k.afg
 Time: 6/11/2015, 9:49, duration 29 min 8 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 39260763, CCD-Z = 430085
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.810	0.829	0.711	1
#50	#40	0.0	100.0	0.649	0.731	0.722	72
#60	#50	0.8	100.0	0.865	0.866	0.773	4438
#70	#60	8.0	99.2	0.912	0.897	0.775	69106
#140	#70	79.0	91.2	0.911	0.908	0.742	2163534
PAN	#140	12.2	12.2	0.869	0.911	0.704	70126096



Mean value SPHT3 = 0.899
 Mean value Symm3 = 0.905
 Mean value b/l3 = 0.725
 Mean value RDNS_C3 = 0.623
 Mean value SPHT_K3 = 0.647

User