


B67_02_SV_14_CRUSH_7K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B67_02_SV_14_CRUSH_7K\B67_02_SV_14_CRUSH_7K109.rdf
 Task file: C:\CamsizerXT\CAMSYS\B67_02_SV_14_CRUSH_7K.afg
 Time: 6/11/2015 , 12:53 , duration 26 min 2 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 39130880 , CCD-Z = 397990
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.1	100.0	0.686	0.751	0.748	152
#60	#50	0.9	99.9	0.863	0.864	0.769	5472
#70	#60	9.0	99.0	0.909	0.896	0.771	76990
#140	#70	78.1	90.0	0.909	0.907	0.739	2095625
PAN	#140	11.9	11.9	0.864	0.908	0.696	74298323



Characteristics

Q3 [%]	x [μm]
10.0	98.3
50.0	159.6
90.0	212.0
SPAN3 = 0.712	
U3 = 1.735	
Mv3(x) = 156.0 μm	
Sigma3(x) = 46.9 μm	

Mean value SPHT3 = 0.897
 Mean value Symm3 = 0.903
 Mean value b/l3 = 0.722
 Mean value RDNS_C3 = 0.609
 Mean value SPHT_K3 = 0.640

User