


B67_2_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B67_2_PRECRUSH\B67_2_PRECRUSH087.rdf
 Task file: C:\CamsizerXT\CAMSYS\B67_2_PRECRUSH.afg
 Time: 6/8/2015 , 11:27 , duration 10 min 50 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 3800660 , CCD-Z = 73950
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.7	100.0	0.709	0.886	0.710	30
#20	#16	1.2	99.3	0.766	0.885	0.717	116
#30	#20	1.6	98.1	0.781	0.879	0.730	499
#40	#30	2.8	96.5	0.803	0.868	0.745	2460
#50	#40	7.7	93.7	0.850	0.872	0.747	20140
#60	#50	9.2	86.0	0.883	0.884	0.746	47241
#70	#60	13.8	76.8	0.906	0.896	0.747	116951
#140	#70	59.9	63.0	0.907	0.909	0.732	1632320
PAN	#140	3.1	3.1	0.866	0.926	0.676	14835909



Characteristics

Q3 [%]	x [μm]
10.0	125.2
50.0	188.8
90.0	343.1
SPAN3 =	1.154
U3 =	1.646
Mv3(x) =	230.5 μm
Sigma3(x) =	165.2 μm

Mean value SPHT3 = 0.885
 Mean value Symm3 = 0.899
 Mean value b/l3 = 0.720
 Mean value RDNS_C3 = 0.523
 Mean value SPHT_K3 = 0.640

User