


BELT_02_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\BELT_02_SV_14_PRECRUSH\BELT_02_SV_14_PRECRUSH101.rdf
 Task file: C:\CamsizerXT\CAMSYS\BELT_02_SV_14_PRECRUSH.afg
 Time: 6/9/2015 , 8:59 , duration 9 min 6 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 1923035 , CCD-Z = 28660
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		1.2	100.0	0.754	0.892	0.736	71
#20	#16	1.4	98.8	0.746	0.879	0.727	226
#30	#20	2.0	97.4	0.768	0.863	0.730	883
#40	#30	3.9	95.4	0.796	0.852	0.735	5258
#50	#40	14.3	91.5	0.860	0.869	0.744	55435
#60	#50	23.6	77.2	0.910	0.901	0.754	183976
#70	#60	28.6	53.6	0.924	0.913	0.746	346033
#140	#70	24.9	25.0	0.917	0.914	0.712	555273
PAN	#140	0.1	0.1	0.852	0.848	0.650	5591918



Characteristics

Q3 [%]	x [μm]
10.0	187.3
50.0	244.9
90.0	396.5
SPAN3 =	0.854
U3 =	1.388
Mv3(x) =	290.1 μm
Sigma3(x) =	177.3 μm

Mean value SPHT3 = 0.891
 Mean value Symm3 = 0.897
 Mean value b/l3 = 0.723
 Mean value RDNS_C3 = 0.488
 Mean value SPHT_K3 = 0.651

User