


BELT_02_SV_14_CRUSH_SPHERE_ROUND

Company:
 User:
 Result file: C:\...LT_02_SV_14_CRUSH_SPHERE_ROUND\BELT_02_SV_14_CRUSH_SPHERE_ROUND108.rdf
 Task file: C:\CamsizerXT\CAMSYS\BELT_02_SV_14_CRUSH_SPHERE_ROUND.afg
 Time: 6/10/2015, 10:07, duration 6 min 27 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 1443172, CCD-Z = 15606
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.464	0.516	0.795	2
#50	#40	0.2	100.0	0.698	0.739	0.709	456
#60	#50	4.2	99.8	0.892	0.882	0.764	17108
#70	#60	33.3	95.6	0.928	0.911	0.767	207243
#140	#70	62.0	62.3	0.920	0.913	0.723	679923
PAN	#140	0.3	0.3	0.912	0.769	0.596	3719359



Mean value SPHT3 = 0.914
 Mean value Symm3 = 0.908
 Mean value b/l3 = 0.724
 Mean value RDNS_C3 = 0.529
 Mean value SPHT_K3 = 0.645

User