


BELT_03_SV_14_PRECRUSH

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDAT\BELT_03_SV_14_PRECRUSH\BELT_03_SV_14_PRECRUSH126.rdf
Task file:	C:\CamsizerXT\CAMSYS\BELT_03_SV_14_PRECRUSH.afg
Time:	6/12/2015 , 12:09 , duration 8 min 9 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 26946808 , CCD-Z = 194228
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		20.0	100.0	0.785	0.874	0.686	1704
#20	#16	23.5	80.0	0.801	0.879	0.670	5609
#30	#20	22.2	56.5	0.813	0.883	0.663	13703
#40	#30	15.3	34.3	0.831	0.889	0.668	26736
#50	#40	9.5	19.0	0.850	0.894	0.679	47030
#60	#50	3.1	9.5	0.864	0.898	0.688	35648
#70	#60	1.9	6.4	0.873	0.900	0.695	37091
#140	#70	2.7	4.5	0.878	0.900	0.700	149817
PAN	#140	1.8	1.8	0.886	0.914	0.748	49600914



Mean value SPHT3 = 0.806
Mean value Symm3 = 0.884
Mean value b/l3 = 0.653
Mean value RDNS_C3 = 0.328
Mean value SPHT_K3 = 0.497

User