


BELT_07_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\BELT_07_SV_14_PRECRUSH\BELT_07_SV_14_PRECRUSH049.rdf
 Task file: C:\CamsizerXT\CAMSYS\BELT_07_SV_14_PRECRUSH.afg
 Time: 5/22/2015, 11:46, duration 9 min 7 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 4833191, CCD-Z = 0
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PD0
> #16		10.6	100.0	0.772	0.880	0.683	357
#20	#16	14.1	89.4	0.799	0.885	0.687	1513
#30	#20	19.1	75.3	0.814	0.886	0.689	5582
#40	#30	17.6	56.2	0.831	0.888	0.694	14154
#50	#40	13.7	38.6	0.848	0.890	0.699	30999
#60	#50	5.4	24.9	0.862	0.892	0.706	27532
#70	#60	4.2	19.5	0.873	0.892	0.713	36111
#140	#70	10.8	15.3	0.893	0.892	0.725	361470
PAN	#140	4.5	4.5	0.942	0.893	0.740	4355471



Characteristics

Q3 [%]	x [μm]
10.0	162.8
50.0	536.1
90.0	1201.8
SPAN3 = 1.938	
U3 = 3.929	
Mv3(x) = 627.0 μm	
Sigma3(x) = 436.8 μm	

Mean value SPHT3 = 0.823
 Mean value Symm3 = 0.887
 Mean value b/l3 = 0.679
 Mean value RDNS_C3 = 0.350
 Mean value SPHT_K3 = 0.555

User