


BELT_09_SV_14_CRUSH_5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\BELT_09_SV_14_CRUSH_5K\BELT_09_SV_14_CRUSH_5K072.rdf
 Task file: C:\CamsizerXT\CAMSYS\BELT_09_SV_14_CRUSH_5K.afg
 Time: 5/27/2015, 11:55, duration 22 min 32 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 28544219, CCD-Z = 257872
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.584	0.718	0.784	3
#40	#30	1.3	100.0	0.861	0.873	0.773	2320
#50	#40	25.3	98.7	0.908	0.903	0.770	112215
#60	#50	36.6	73.4	0.920	0.912	0.759	291185
#70	#60	21.7	36.8	0.918	0.913	0.733	256650
#140	#70	12.2	15.1	0.897	0.903	0.705	393534
PAN	#140	2.9	2.9	0.837	0.897	0.676	49233745



Characteristics

Q3 [%]	x [μm]
10.0	190.8
50.0	266.9
90.0	341.9
SPAN3 = 0.566	
U3 = 1.467	
Mv3(x) = 265.2 μm	
Sigma3(x) = 68.1 μm	

Mean value SPHT3 = 0.906
 Mean value Symm3 = 0.906
 Mean value b/l3 = 0.734
 Mean value RDNS_C3 = 0.601
 Mean value SPHT_K3 = 0.672

User