


BELT_09_SV_14_CRUSH_6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\BELT_09_SV_14_CRUSH_6K\BELT_09_SV_14_CRUSH_6K068.rdf
 Task file: C:\CamsizerXT\CAMSYS\BELT_09_SV_14_CRUSH_6K.afg
 Time: 5/26/2015 , 12:55 , duration 29 min 46 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 34786884 , CCD-Z = 346930
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0	0.695	0.805	0.684	2
#30	#20	0.0	100.0	0.691	0.845	0.719	4
#40	#30	0.1	100.0	0.704	0.762	0.725	57
#50	#40	16.0	99.9	0.915	0.905	0.784	76631
#60	#50	39.4	83.9	0.922	0.912	0.763	303853
#70	#60	25.1	44.5	0.920	0.914	0.737	285162
#140	#70	14.8	19.4	0.898	0.904	0.707	463807
PAN	#140	4.6	4.6	0.849	0.902	0.689	90490297



Characteristics

Q3 [%]	x [μm]
10.0	169.5
50.0	256.3
90.0	312.0
SPAN3 = 0.556	
U3 = 1.579	
Mv3(x) = 247.0 μm	
Sigma3(x) = 63.4 μm	

Mean value SPHT3 = 0.909
 Mean value Symm3 = 0.908
 Mean value b/l3 = 0.735
 Mean value RDNS_C3 = 0.614
 Mean value SPHT_K3 = 0.674

User