


## BELT\_09\_SV\_14\_SPHER\_ROUND

Company:	
User:	
Result file:	C:\...izerXT\CAMDAT\BELT_09_SV_14_SPHER_ROUND\BELT_09_SV_14_SPHER_ROUND106.rdf
Task file:	C:\CamsizerXT\CAMSYS\BELT_09_SV_14_SPHER_ROUND.afg
Time:	5/21/2015 , 14:37 , duration 5 min 58 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 989219 , CCD-Z = 0
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDO
> #16		0.0	100.0				0
#20	#16	0.0	100.0	0.725	0.899	0.691	2
#30	#20	0.0	100.0				0
#40	#30	0.1	100.0	0.571	0.661	0.736	28
#50	#40	3.9	99.9	0.865	0.865	0.759	11310
#60	#50	44.5	96.0	0.915	0.904	0.768	219299
#70	#60	42.1	51.5	0.914	0.909	0.730	287056
#140	#70	9.3	9.4	0.881	0.905	0.639	88636
PAN	#140	0.1	0.1	0.889	0.883	0.656	382888



Mean value SPHT3 = 0.903
Mean value Symm3 = 0.903
Mean value b/l3 = 0.727
Mean value RDNS_C3 = 0.575
Mean value SPHT_K3 = 0.657

User