


BELT_11_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\BELT_11_SV_14_PRECRUSH\BELT_11_SV_14_PRECRUSH080.rdf
 Task file: C:\CamsizerXT\CAMSYS\BELT_11_SV_14_PRECRUSH.afg
 Time: 6/8/2015 , 10:30 , duration 12 min 52 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 4085822 , CCD-Z = 91945
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		1.6	100.0	0.785	0.884	0.745	124
#20	#16	2.7	98.4	0.787	0.875	0.724	551
#30	#20	7.0	95.7	0.836	0.874	0.746	4429
#40	#30	31.8	88.7	0.898	0.904	0.757	55451
#50	#40	36.5	56.9	0.914	0.915	0.743	148553
#60	#50	7.7	20.4	0.913	0.913	0.733	70667
#70	#60	3.8	12.7	0.914	0.909	0.736	58059
#140	#70	8.2	8.9	0.906	0.910	0.741	461726
PAN	#140	0.7	0.7	0.890	0.928	0.724	22647608



Characteristics

Q3 [%]	x [μm]
10.0	224.4
50.0	403.6
90.0	621.1
SPAN3 = 0.983	
U3 = 1.937	
Mv3(x) = 431.9 μm	
Sigma3(x) = 208.9 μm	

Mean value SPHT3 = 0.892
 Mean value Symm3 = 0.906
 Mean value b/l3 = 0.733
 Mean value RDNS_C3 = 0.567
 Mean value SPHT_K3 = 0.674

User