


BELT_12_SV_14_CRUSH6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\BELT_12_SV_14_CRUSH6K\BELT_12_SV_14_CRUSH6K137.rdf
 Task file: C:\CamsizerXT\CAMSYS\BELT_12_SV_14_CRUSH6K.afg
 Time: 6/15/2015, 14:37, duration 22 min 45 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 59151260, CCD-Z = 711106
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.4	100.0	0.847	0.862	0.778	987
#50	#40	20.9	99.6	0.912	0.904	0.782	120986
#60	#50	34.9	78.7	0.923	0.913	0.764	349829
#70	#60	21.7	43.8	0.920	0.914	0.739	326089
#140	#70	15.7	22.1	0.898	0.903	0.710	699745
PAN	#140	6.4	6.4	0.851	0.902	0.692	101816818



Characteristics

Q3 [%]	x [μm]
10.0	144.7
50.0	258.1
90.0	327.6
SPAN3 = 0.708	
U3 = 1.875	
Mv3(x) = 248.3 μm	
Sigma3(x) = 74.1 μm	

Mean value SPHT3 = 0.906
 Mean value Symm3 = 0.908
 Mean value b/l3 = 0.736
 Mean value RDNS_C3 = 0.608
 Mean value SPHT_K3 = 0.678

User