


BELT\_12\_SV\_14\_SHERE\_AND\_ROUND

Company:	
User:	
Result file:	C:\...MDAT\BELT_12_SV_14_SHERE_AND_ROUND\BELT_12_SV_14_SHERE_AND_ROUND124.rdf
Task file:	C:\CamsizerXT\CAMSYS\BELT_12_SV_14_SHERE_AND_ROUND.afg
Time:	6/12/2015 , 11:44 , duration 5 min 0 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 1182506 , CCD-Z = 16417
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.515	0.676	0.677	18
#50	#40	3.1	100.0	0.848	0.852	0.749	8044
#60	#50	40.3	96.9	0.919	0.907	0.769	191772
#70	#60	45.8	56.6	0.921	0.913	0.734	293179
#140	#70	10.6	10.8	0.886	0.908	0.638	94347
PAN	#140	0.2	0.2	0.925	0.781	0.708	8468300



Mean value SPHT3 = 0.908
Mean value Symm3 = 0.906
Mean value b/l3 = 0.726
Mean value RDNS_C3 = 0.578
Mean value SPHT_K3 = 0.651

User